

PCE Americas Inc.
711 Commerce Way
Suite 8
Jupiter
FL-33458
USA
From outside US: +1
Tel: (561) 320-9162
Fax: (561) 320-9176
info@pce-americas.com

PCE Instruments UK Ltd.
Units 12/13
Southpoint Business Park
Ensign way
Hampshire / Southampton
United Kingdom, SO31 4RF
From outside UK: +44
Tel: (0) 2380 98703 0
Fax: (0) 2380 98703 9
info@oce-instruments.com

www.pce-instruments.com/english www.pce-instruments.com

Technical Surface Testing PCE-COM 20

PCE-COM 20 Conductivity Tester for Metals

Large measuring range up to 112% IACS or 65 MS/m with lift-off and temperature compensation, memory, PC-compatible software, factory calibration certificate and 60 kHz operating frequency

PCE-COM 20 is a portable handheld non-destructive conductivity tester for metals. This non-destructive testing (NDT) device uses eddy current to determine the electrical conductivity of non-ferrous metals such as aluminum and copper.

Featuring an operating frequency of 60 kHz, the conductivity meter has a large measuring range of 0.51 \dots 112% IACS with an accuracy of +/- 0.5% at 20 ° C / 68 ° F. Thanks to a resolution of up to 0.01% IACS, automatic temperature compensation (ATC) and lift-off compensation (up to 500 μ m), the device ensures quick, easy, accurate and reproducible measurements of coated or corroded pieces during changing ambient conditions.

Measurement of the electrical conductivity of non-ferrous metals, such as aluminum, copper, titanium, magnesium or bronze, is necessary in applications involving electrical conductors and the characterization of alloys. Typical application areas are the assessment of strength differences in heat-treated or hardened materials, the authenticity testing of coin alloys, the verification of alloy inhomogeneities in critical components and the sorting of materials.

The conductivity meter is powered by an internal battery that can be charged via the interface on the bottom of the unit. In addition to the connection for the charging adapter, there is a USB interface allowing for the transfer of measurement data to a PC for more detailed analysis.

- Eddy current measuring principle
- For non-ferrous metals and alloys
- Non-destructive testing (NDT)
- 60 khZ operating frequency
- Large measuring range up to 112% IACS or 65 MS/m
- Memory for up to 500 groups of measurements
- Automatic temperature compensation (ATC)
- Lift-off compensation up to 500 μm
- Automatic calibration
- Adjustable backlighting

- Internal rechargeable battery
- Portable, handheld
- User friendly

Technical specifications:

Operating frequency 60 kHz, sine wave

0.51% IACS ... 112% IACS

Conductivity measuring range 0.3 MS/m ... 65 MS/m

Resistance range $0.015388 \dots 3.33333 \Omega \bullet mm^2 / m$

Conductivity measuring 0.01% IACS (at <51% IACS)

resolution 0.1% IACS (at 51% IACS ... 112% IACS)

Conductivity measuring $\pm 0.5\%$ at $+20 \degree$ C / $+68 \degree$ F

accuracy \pm 1% in the range 0 ... +40 ° C / +32 ... +104 ° F

Lift-off compensation $0.5 \text{ mm} / \approx 0.0197$ "

Temperature measuring range 0 ... + 50 ° C / +32 ... +122 ° F

Temperature measuring

accuracy

 \pm 0.5 $^{\circ}$

Automatic adjustment of conductivity result to the value at 20 ° C /

Temperature compensation

+68 ° F

Operating conditions $0 \dots + 50 \,^{\circ} \,^{\circ} \,^{\circ} \,^{\circ} \,^{\circ} + 32 \dots + 122 \,^{\circ} \,^{$

Display LCD, backlit

Menu languages English, German, Chinese (simplified)

Power supply Internal, rechargeable battery

Probe diameter Ø 14 mm / ≈ 0.55 "

Memory Stores up to 500 groups of measurement values

Data interface USB port connection

Dimensions $\approx 220 \times 95 \times 35 \text{ mm} / 8.66 \times 3.74 \times 1.38$ "

Weight $\approx 415 \text{ g} / 1 \text{ lb (with probe)}$

Delivery contents:

1 x PCE-COM 20 conductivity tester for metals

1 x sine wave measuring probe

1 x set of calibration plates

1 x factory calibration certificate

1 x PC-compatible software

1 x USB to RS-232 data cable

1 x charging adapter

1 x hex wrench

1 x carrying case

1 x user manual